

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-028491

(43)Date of publication of application : 29.01.2002

(51)Int.Cl.

B01J 27/182
B01J 27/19
B01J 32/00
C07B 61/00
C10G 45/08
C10G 47/12
// C07C 4/06
C07C 7/148

(21)Application number : 2000-211384

(71)Applicant : CATALYSTS & CHEM IND CO LTD

(22)Date of filing : 12.07.2000

(72)Inventor : OHAMA KOICHI

(54) FORMED CATALYST FOR HYDROGENATION TREATMENT AND PRODUCING METHOD THEREOF

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a formed catalyst for hydrogenation treatment which exhibits excellent desulfurizing and decomposing activity when used for the hydrogenation treatment of hydrocarbon oils, in particular, a reduced pressure light oil, a light oil and a kerosine, etc., and has excellent properties, and a producing method thereof.

SOLUTION: This formed catalyst for hydrogenation treatment is formed by depositing at least one kind of metallic component selected from the Periodic Table group IVa and VIII on a phosphate-silica-alumina carrier and has the following properties 1-7: 1. Surface area is ≥ 300 m²/g. 2. Pore volume is 0.45-0.80 ml/g. 3. Bulk specific gravity is 0.45-0.80 g/ml. 4. Average pore diameter is 60-90 μ m. 5. The pore ratio of ≥ 100 μ m is $\geq 15\%$. 6. The value of [pore volume (PV) occupied by pores of the average pore diameter ± 10 μ m] $\times 100$ / [pore volume occupied by pores of \geq pore diameter 34 μ m] is $\geq 50\%$. 7. Mechanical strength is ≥ 7 N/mm.

LEGAL STATUS

[Date of request for examination]

26.04.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]


[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]



Copyright (C); 1998,2003 Japan Patent Office